

AB-0716-T
TURT190209891
11-19

TEST REPORT

REPORT NUMBER : TURT190209891
APPLICANT NAME Fargotex Sp ZO.O. (\$)
ADDRESS Aleja Legionow114 C 18-400 NIP:7181721036 Lomza / POLAND
Fax No: +48 86 218 51 44
Tel: +48 86 218 53 90
ATTENTION : Ewelina Slaby (eslaby@fargotex.pl)
Barbara Mickunas, Tic Operations
(barbara.mickunas@intertek.com;tic.operations@intertek.com)

SAMPLE DESCRIPTION : One sample of navy/brown woven fabric
DATE IN : 20 November, 2019 (13:59)
DATE OUT : 26 November, 2019
FIBER COMPOSITION : Claimed to be 100% Polyester
BATCH NO : ZOYA
MODEL STYLE NO : ZOYA
CARE INSTRUCTION : Not Given

TEST	SAMPLE
Flammability test	P

P = MEETS BUYER' S REQUIREMENT / F = DOES NOT MEET BUYER' S REQUIREMENT / NR = NO REQUIREMENT / SC=STILL CONTINUES / X=NOT PERFORMED / NA = NOT APPLICABLE/ LS : LACK OF SAMPLE

This report (including any enclosures and attachments) are prepared for the exclusive use of the Customer(s) named in the report and solely for the purpose for which it is provided and on the basis of instructions and information and/or materials supplied by Intertek's Customer. The test results relate only to the specific items tested and are not intended to be a recommendation for any particular course of action. Customer is responsible for acting as it sees fit on the basis of such results. Unless Intertek provide express prior written consent, no part of this report should be reproduced, distributed or communicated to any third party, nor could it be used for PR activities. Intertek do not accept any liability if this report is used for an alternative purpose from which it is intended, nor do Intertek owe any duty of care to any third party in respect of this report. Except where explicitly agreed in writing, all work and services performed is governed by Intertek Standard Terms and Conditions of Service which is available on request or can be obtained at <http://www.intertek.com/terms>. Testing reports without signature are not valid. The sample has been provided by the customer and the results apply to the sample as received. Sample information is supplied by the customer. Unless otherwise requested, this laboratory applies shared risk decision rule. Tests marked (*) in this test report are not included in the TURKAK accreditation schedule for this laboratory.



Ayda Çetinkaya
Customer Care Executive



Nida Arslanbay
Textile Laboratory Manager

Intertek Test Hizmetleri A.S.
Merkez Mahallesi Sanayi Cad. No.23 Altındag Plaza Yenibosna-34197/ISTANBUL
Phone : +90 212 496 46 46 Fax: +90 212 452 80 55
e-mail : intertekcg.turkiye@intertek.com
<http://www.intertek-turkey.com>



190209891

Test Method	Result	Requirements
-------------	--------	--------------

FLAMMABILITY TEST

BS 5852: 1979 Part 1

Test Specification

Test Method: BS 5852-1: 1979 as modified by Shedule 4 Part 1 and Schedule 5 Part 1 of The Furniture and Furnishing (fire) (safety) Regulations 1988 (as amended)
Criteria of Ignition: Ignition Source 0: Calibrated Senior Service Cigarette
 Ignition Source 1: Butane Gas flowing at 45ml/minute @25°C
Flame Application Time: 20±1 seconds
Side Tested: Face

Filling Type: Polyurethane foam
Size: 450 x 300 x 75 mm (Back) & 450x150x 75 mm (seat)
Density/Hardness: 20-22 kg/m³, Type B Hardness grade130

Pre-treatment / Durability procedure: None

Conditioning

Prior to testing:	At least 72 hours in ambient indoor conditions, then at least 16 hours in an atmosphere having a temperature of 20±5°C and a relative humidity of 50±20%
At time of testing:	Temperature of 15°C to 30°C and a relative humidity of 20% to 70%

Test Method	Pre Treatment	Flammability Performance Requirements	Result
BS 5852: Part 1: 1979, Ignition source 0 (Cigarette)	None	Compliance with Schedule 4 Part 1 (The cigarette test) of The Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended).	PASS

Note: Fabric was submitted for test rather than the upholstery composite so as suggested by The Guide to the Furniture Regulations the cover fabric was tested for cigarette resistance using standard polyurethane foam (non-modified) as this will give the furniture manufacturer a good indication of its likelihood to pass the cigarette test for the finished article.

RESULTS

Page 3 of 4

REPORT :TURT190209891

26 November, 2018

Test Method	Result	Requirements
-------------	--------	--------------

Test Result:

"The following test results relate only to the ignitability of the combination of materials under the particular conditions of test; they are not intended as a mean of assessing the full potential fire hazard of materials in use."

Cigarette Test	Specimen No	Cigarette Burning Time	Flaming	Progressive Smouldering	Covering Splitting	Result
	1	26 min 15 sec	N	Y	Y	Pass
	2	27 min 43 sec	N	Y	Y	Pass

Y: Yes N: No NA: Not Applicable P: Pass F: Fail D: Depth L: Length W: Width

Conclusions:

The composite tested meets the requirements of Schedule 4 Part 1 of the Furniture and Furnishings (fire) (safety) Regulations 1988 (as amended). **PASS.**

END OF TEST REPORT

RESULTS

Page 4 of 4

REPORT :TURT190209891

26 November, 2018

Test Method	Result	Requirements
-------------	--------	--------------