

CAIRO

Composition

Weight

♦ Width

Se Article

23

100% PES

300 g/m² +/- 5%

144 cm +/- 2 cm

Furniture fabric





Product characteristics in accordance with the PN-EN 14465:2005+A1:2007

Standard	Standard value	Category
EN ISO 13936-2 (mm)	≤4	Α
EN ISO 13934 -1 (N)	≥400	B
EN ISO 12947 -2 (rubs)	≥45 000	Α
EN ISO 12945 -2 (assessment after 5000 rubs)	≥5	A
	EN ISO 13936-2 (mm) EN ISO 13934 -1 (N) EN ISO 12947 -2 (rubs) EN ISO 12945 -2	EN ISO 13936-2 (mm) ≤4 EN ISO 13934 -1 (N) ≥400 EN ISO 12947 -2 (rubs) ≥45 000 EN ISO 12945 -2 >5

Pilling is a natural process; it is not possible to eliminate it completely.
For technological reasons fabric colour may differ from that in the catalogue.
Dark and intensive fabric colours will migrate onto the light colours.
The results of the Technical Specification are average results obtained during the tests.
Exposure to UV rays may cause change of colours.



Idesin M. Siwek Spółka Jawna, ul. Batalionów Chłopskich 91A, 25-671 Kielce, tel: +48 698 171 888, e-mail: kontakt@idesin.pl